

TEMPERATURE DEPENDENCE OF THE UPPER CRITICAL
FIELD IN HIGH-TEMPERATURE SUPERCONDUCTORS:
LOCALIZATION EFFECTS.

E.Z.Kuchinskii, M.V.Sadovskii

Institute for Electrophysics, Russian Academy of Sciences, Ural Branch,

Ekaterinburg, 620219, Russia

It is shown that the anomalous temperature dependence of the orbital part of the upper critical field H_{c2} observed for epitaxially grown films of high-temperature superconductor $Bi - Sr - Cu - O$ (in wide temperature interval) can be satisfactorily explained by the influence of localization effects in two-dimensional (quasi-two-dimensional) case.

In a recent paper Osofsky et al. [1] presented the unique data on the temperature dependence of the upper critical field of high-temperature superconductor $Bi_2Sr_2CuO_y$ in wide temperature interval from $T_c \approx 19K$ to $T \approx 0.005T_c$, which has shown rather anomalous dependence with negative curvature at any temperature. The authors of [1] has noted that this type of behavior is difficult to explain within any known theory. It is sharply different from the standard behavior of BCS-model, as well as from that predicted by the model of compact charged Bosons (bipolarons) [2]. In this latter case H_{c2} there appears a power-like divergence for $T \rightarrow 0$, while

the experimental value of $H_{c2}(T = 0)$ is apparently finite. The aim of the present work is to demonstrate that the observed dependence of $H_{c2}(T)$ can be satisfactorily explained by localization effects in two-dimensional (quasi-two-dimensional) model in the limit of sufficiently strong disorder [3]. Measurements of H_{c2} in Ref. [1] were performed on epitaxially grown films of $Bi_2Sr_2CuO_y$, however it is quite possible that the films were still disordered enough, which can be guessed from rather wide ($\sim 7K$) superconducting transition. Unfortunately the relevant data, in particular on the value of conductivity of the films studied are absent. This gives us some grounds to try to interpret the data obtained in Ref. [1] in the framework of rather strong disorder the effects of which are obviously enhanced by the quasi-two-dimensional nature of high-temperature superconductors.

Below we shall limit ourselves by description of purely two-dimensional case because the appropriate dependences for quasi-two-dimensional system differ only very slightly for the relevant values of parameters of the model [3]. The general approach to H_{c2} -behavior in strongly disordered systems was given in Ref. [4].

To describe the electronic properties of strongly disordered system in external magnetic field we need following Matsubara-type two-particle Green's functions in diffusion and Cooper channels for small q and ω_m :

$$\begin{pmatrix} \Phi_E(\mathbf{q}\omega_m = 2\varepsilon_n) \\ \Psi_E(\mathbf{q}\omega_m = 2\varepsilon_n) \end{pmatrix} = - \frac{N(E)}{i|\omega_m| + i \begin{pmatrix} D_1(\omega_m) \\ D_2(\omega_m) \end{pmatrix} q^2} \quad (1)$$

Here $\omega_m = 2\pi mT$, $\varepsilon_n = 2\pi(n + \frac{1}{2})T$ —are Matsubara frequencies, $N(E)$ —the electronic density of states at the Fermi level E . The generalized "diffusion coefficients" D_1 D_2 are in general unequal in the presence of magnetic field which breaks time-invariance. In this case we have to consider the coupled system of equations for both Green's functions.

In the following we shall be interested only in the case of magnetic field perpendicular to the highly conducting planes. From the standard approach to supercon-

ducting transition in external magnetic field [5] we obtain the following equation for temperature dependence of $H_{c2}(T)$:

$$\ln \frac{T}{T_c} = 2\pi T \sum_{\varepsilon_n} \left\{ \frac{1}{2|\varepsilon_n| + 2\pi D_2(2|\varepsilon_n|)\frac{H}{\Phi_0}} - \frac{1}{2|\varepsilon_n|} \right\} \quad (2)$$

where $\Phi_0 = \frac{\pi c}{e}$ —is magnetic flux quantum, T_c —is BCS transition temperature in the absence of magnetic field.

It is seen from Eq.(2) that the anomalies in behavior of the upper critical field are related to the frequency dependence of diffusion coefficient which becomes non-trivial close to the Anderson metal-insulator transition.

Within the approach based upon self-consistent theory of localization [6,7] the system of equations for diffusion coefficients in magnetic field in two- dimensional case takes the following form [8]:

$$\begin{aligned} \frac{D_0}{D_2} &= 1 + \frac{1}{\pi N(E)} \sum_{|\mathbf{q}| < q_0} \frac{1}{\omega + D_1 q^2} \\ \frac{D_0}{D_1} &= 1 + \frac{1}{\pi N(E)} \sum_{|\mathbf{k}| < q_0} \frac{1}{\omega + D_2 k^2} \end{aligned} \quad (3)$$

where $k^2 = 4m\omega_H(n + \frac{1}{2})$, $\omega_H = \frac{eH}{mc}$ — is the cyclotron frequency, n —is Landau's quantum number, q_0 — is the cut-off momentum ($q_0 \approx l^{-1}$), defined by $D_0 q_0^2 = \frac{1}{2\tau}$, where D_0 —is the usual Drude diffusion coefficient, τ^{-1} —is the mean free time and l —is the mean free path.

Let us introduce $d_1 = \frac{D_1}{D_0}$, $d_2 = \frac{D_2}{D_0}$ and dimensionless disorder parameter $\lambda = \frac{1}{2\pi E\tau}$. Then Eqs.(3) are rewritten as:

$$\begin{aligned} \frac{1}{d_2} &= 1 + \frac{\lambda}{d_1} \ln(1 + d_1 \frac{1}{2\omega\tau}) \\ \frac{1}{d_1} &= 1 + \frac{\lambda}{d_2} \sum_{n=0}^{N_0} \frac{1}{n + \frac{1}{2} + \frac{\omega}{4m\omega_H D_0} \frac{1}{d_2}} \end{aligned} \quad (4)$$

where $N_0 = \frac{1}{8m\omega_H D_0 \tau}$ —is the maximal number of Landau levels determined by the cutoff.

With accuracy sufficient for the use in Eq.(2), the solution of Eqs. (4) for diffusion coefficient in Cooper channel in small magnetic fields when $\omega_H \ll \frac{\lambda e^{-1/\lambda}}{\tau}$, can be written in the following form [3]:

$$d_2 = \begin{cases} 1 & \omega \gg \frac{e^{-1/\lambda}}{2\tau} \\ 2\omega\tau e^{1/\lambda} & \omega \ll \frac{e^{-1/\lambda}}{2\tau} \end{cases} \quad (5)$$

and in fact we can neglect the magnetic field influence upon diffusion.

It is easy to see that the anomalies of the upper critical field due to the frequency dependence of diffusion coefficient will appear only for temperatures $T \ll \frac{e^{-1/\lambda}}{\tau}$ [3]. For higher temperatures we obtain the usual behavior of "dirty" superconductors. Superconductivity survive in a system with finite localization length if the following inequality holds $T_c \gg \lambda \frac{e^{-1/\lambda}}{\tau}$ [3], which is equivalent to the well known criteria [9] of the smallness of Cooper pair size compared with localization length. This latter length is exponentially large in two- dimensional systems with small disorder ($\lambda \ll 1$). The most interesting (for our aims) limit of relatively strong disorder is defined by $T_c \ll \frac{e^{-1/\lambda}}{\tau}$, so that in fact we are dealing with pretty narrow region of λ 's when $\lambda \frac{e^{-1/\lambda}}{\tau} \ll T_c \ll \frac{e^{-1/\lambda}}{\tau}$. In this case the upper critical field is defined by the equation ($\gamma = 1.781$)[3]:

$$\ln \left(\frac{\gamma}{2\pi} \frac{e^{-1/\lambda}}{\tau T} \right) = (1 + 4\pi \frac{D_0}{\Phi_0} \frac{\tau H_{c2}}{e^{-1/\lambda}}) \ln \left(\frac{\gamma}{2\pi} \frac{e^{-1/\lambda}}{\tau T_c} (1 + 4\pi \frac{D_0}{\Phi_0} \frac{\tau H_{c2}}{e^{-1/\lambda}}) \right) \quad (6)$$

from which we can directly obtain the $T(H_{c2})$ —dependence. The appropriate behavior of the upper critical field for two sets of parameters is shown in Fig.1. The curve of $H_{c2}(T)$ demonstrates negative curvature and H_{c2} diverges for $T \rightarrow 0$. This weak (logarithmic) divergence is connected with our neglect of the magnetic field influence upon diffusion [3]. Taking this influence into account we can suppress this divergence of H_{c2} as $T \rightarrow 0$ and we obtain:

$$H_{c2}(T = 0) = \frac{\gamma}{2\pi} \frac{\Phi_0}{D_0} \frac{1}{\tau} \quad (7)$$

This is the main effect of broken time invariance and it is clear that it is important only for extremely low temperatures [3]. In the following we neglect it.

For the quasi-two-dimensional case on the dielectric side of Anderson's transition, but not too very close to it, the behavior of diffusion coefficient is quite close to that of purely two-dimensional case, so that the upper critical field can be analyzed

within two-dimensional approach. Close to the transition (e.g. over interplane transfer integral) both for metallic and insulating sides and for parameters satisfying the inequality $\lambda \frac{e^{-1/\lambda}}{\tau} \ll T_c \ll \frac{e^{-1/\lambda}}{\tau}$, the temperature dependence of H_{c2} is in fact again very close to those in purely two-dimensional case considered above [3]. Some deviations appear only in a very narrow region of very low temperatures [3]. The details can be found in Ref. [3].

These anomalies of H_{c2} —behavior are always due to the appropriate anomalies of frequency dependence of the generalized diffusion coefficient close to the Anderson transition and in this sense just reflect the change in the nature electronic states in the region of metal-insulator transition.

In Fig.1 we also show the experimental data for H_{c2} from Ref.[1]. Theoretical curve (1) is given for the parameters which lead to rather good agreement with experiment in the low temperature region. The curve (2) corresponds to parameters giving good agreement in a wide temperature region except the lowest temperatures. The cyclotron mass m was always assumed to be equal that of the free electron. In general we observe satisfactory agreement between theory and experiment. Unfortunately, the values of the ratio $\frac{e^{-1/\lambda}}{T_c \tau}$ for the second curve, while corresponding to quite reasonable values of λ , lead to nonrealistic (too small) values of $T_c \tau$, which are rather doubtful for the system with relatively high T_c . For the first curve situation is much better though the size of electron damping on the scale of T_c is still very large which corresponds to strong disorder. Note however, that the detailed discussion of these parameters is actually impossible without the knowledge of additional characteristics of the films studied in Ref. [1]. In particular it is quite interesting to have an independent estimate of λ . We also want to stress relatively approximate nature of these parameters due to our two- dimensional idealization. More serious comparison should be done using the expressions of Ref. [3] for the quasi-two-dimensional case, which again requires the additional information on the system, in particular, the data on the anisotropy of electronic properties.

In our opinion the relatively good agreement of experimental data of Ref. [1] with

theoretical dependences obtained for the two-dimensional (quasi-two- dimensional) case of disordered system with Anderson localization illustrates the importance of localization effects for the physics of high- temperature superconductors [10].

The authors are grateful to Dr. I.Bozovic for sending the preprint of Ref.[1] before its publication. This work is supported by Russian Foundation for Fundamental Research under the grant N° 93-02-2066.

REFERENCES

- ¹ Osofsky M.S., Soulen R.J., Wolf S.A., Broto J.M., Rakoto H., Ousset J.C., Coffe G., Askenazy S., Pari P., Bozovic I., Eckstein J.N., Virshup G.F., Ginzton E.L.—Phys.Rev.Lett., **71**, 2315 (1993)
- ² Aleksandrov A.S., Krebs A.B.—Uspekhi Fiz. Nauk **162**, 1 (1992)
- ³ Kuchinskii E.Z., Sadovskii M.V.—Superconductivity: Physics, Chemistry, Technology **6**, 1119 (1993)
- ⁴ Kuchinskii E.Z., Sadovskii M.V.—Superconductivity: Physics, Chemistry, Technology **4**, 2278 (1991)
- ⁵ De Gennes P.G. Superconductivity of Metals and Alloys. W.A.Benjamin, NY, 1966.
- ⁶ Vollhardt D., Wölfle P.—Phys.Rev. **B22**, 4666 (1980)
- ⁷ Sadovskii M.V.—Soviet Scientific Reviews. Ed. by I.M.Khalatnikov, v.7, p.1, Harwood Academic Publ., NY, 1985.
- ⁸ Yoshioka D., Ono Y., Fukuyama H.—J.Phys.Soc.Japan **50**, 3419 (1981)
- ⁹ Bulaevskii L.N., Sadovskii M.V.—J.Low-Temp.Phys. **59**, 89 (1985)
- ¹⁰ Sadovskii M.V.—In "Studies of High-Temperature Superconductors". Vol.11. Ed. by A.V.Narlikar. Nova Science Publishers, NY, 1993.

Figure Captions:

Fig.1 Temperature dependence of the upper critical field:

Theoretical curve (1) is given for the case of $\frac{e^{-1/\lambda}}{T_c\tau} = 2$, $\lambda = 0.18$, while the curve (2) is for $\frac{e^{-1/\lambda}}{T_c\tau} = 20$, $\lambda = 0.032$.

Squares—experimental data of Ref. [1].